

SPECIFICATION SHEET

SEPIOLITE 30-60 Industrial Absorbent

Composition (XRD)

Sepiolite	65% (Min. 60%)
------------------	----------------

Physical properties

Density	0.65 g/cc (Max. 0.72 g/cc)
----------------	----------------------------

Westinghouse water absorption	145% (Min. 100%)
--------------------------------------	------------------

Westinghouse oil absorption	80% (Min. 60%)
------------------------------------	----------------

Particle size distribution

> 850 microns	Max. 1%
-------------------------	---------

850 - 150 microns	Min. 97.5%
--------------------------	------------

< 150 microns	Max. 1.5%
-------------------------	-----------